



PIGMENT PERFORMANCE DATA

955
UNIVERSAL DISPERSIONS

PRODUCT NUMBER	PRODUCT NAME	COLOR INDEX NAME	LIGHT RESISTANCE		HEAT RESISTANCE 30 Min @ ° F	SOLVENT RESISTANCE				CHEMICAL RESISTANCE		OVERSTRIPE RESISTANCE Nitrocellulose
			Full Shade	Tint		Aliphatic	Aromatic	Ketone	Alcohol	Acid	Base	
955-34120	Phthalo Blue RS	Blue 15:1	5	5	390	5	5	5	5	5	5	5
955-34250	Indanthrone Blue	Blue 60	5	5	390	5	5	5	5	5	5	5
955-34520	Phthalo Blue GS	Blue 15:3	5	5	390	5	5	5	5	5	5	5
955-34860	Phthalo Green BS	Green 7	5	5	390	5	5	5	5	5	5	5
955-35080	Chrome Oxide Green	Green 17	5	5	>390	5	5	5	5	5	5	5
955-35160	Phthalo Green YS	Green 36	5	5	390	5	5	5	5	5	5	5
955-35410	Bright Yellow 151	Yellow 151	5	4-5	390	5	4-5	4-5	4-5	5	3	5
955-35440	Bright Yellow GS	Yellow 175	5	4-5	360	5	5	3-4	4-5	5	5	5
955-35470	Bright Yellow RS	Yellow 83	4D	4	390	5	3-4	3-4	4-5	5	5	5
955-35560	Bright Yellow BV	Yellow 184	5	4	> 390	5	5	5	5	3-4	5	5
955-35580	Trans Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5	5
955-35670	Permanent Yellow RS	Yellow 110	5	5	390	5	5	4	5	5	5	5
955-35780	Yellow Oxide	Yellow 42	5	5	320	5	5	5	5	5	5	5
955-35920	Chroma Orange	NA	4-5	4	350	5	5	4	4	5	5	5
955-35930	Durable Orange	Orange 36	5	4-5	320	5	4-5	4-5	4-5	5	5	5
955-35950	Bright Orange	Orange 34	3-4D	2	390	4-5	3	3-4	5	5	5	5
955-36500	Bright Red 170	Red 170	4D	3-4	320	5	4-5	4	4-5	5	5	5
955-36530	Chroma Red	Red 254	5	5	390	5	5	5	5	5	5	5
955-36540	Deep Red 170	Red 170	3D	2	320	5	4-5	3	4	5	5	5
955-36590	Perylene Red	Red 224	5	5	390	5	5	5	5	5	4-5	5
955-36640	Brilliant Red	NA	5	5	390	5	5	5	5	5	5	5
955-36420	Trans Red Oxide	Red 101	5	5	> 390	5	5	5	5	5	5	5
955-36760	Red Oxide	Red 101	5	5	> 390	5	5	5	5	5	5	5
955-37100	Quinacridone Violet	Violet 19	4-5	4-5	390	5	5	4-5	4-5	5	5	5
955-37200	Perylene Violet	Violet 29	5	5	390	5	5	5	5	5	4-5	5
955-37250	Perylene Maroon	Red 179	5	5	390	5	5	5	5	5	4-5	5
955-37470	Carbazole Violet	Violet 23	4-5	3-4	320	5	4-5	4	5	5	5	5
955-37500	Quinacridone Magenta	Red 122	4D	4-5	390	5	5	4-5	5	5	5	5
955-39050	Conductive Black	Black 7	5	5	> 390	5	5	5	5	5	5	5
955-39230	Tinting Black	Black 7	5	5	> 390	5	5	5	5	5	5	5
955-39231	Shading Black	Black 7	5	5	390	5	5	5	5	5	5	5
955-39331	Jet Black	Black 7	5	5	> 390	5	5	5	5	5	5	5
955-39600	TiO ₂ White	White 6	5	5	> 390	5	5	5	5	5	5	5

LEGEND:

D – Darkens
5 – Excellent
4 – Very Good

3 – Good
2 – Fair
1 – Poor

Dated: 23 December 14
Supersedes: 27 February 07